

(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 983 837 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
08.03.2000 Bulletin 2000/10

(51) Int. Cl.⁷: B29D 11/00, G02B 1/04

(21) Application number: 98123191.3

(22) Date of filing: 04.12.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 02.09.1998 US 145654

(71) Applicant: INNOVA, Inc
Hsinchu (TW)

(72) Inventor: Wang, Joe
Hsinchu (TW)

(74) Representative:
Winter, Brandl, Fürniss, Hübner, Röss,
Kaiser, Polte, Kindermann
Partnerschaft
Patent- und Rechtsanwaltskanzlei
Alois-Steinecker-Strasse 22
85354 Freising (DE)

(54) Method for preparation for colored contact lens

(57) A method for preparation of colored contact lens with an embedded pattern is disclosed. Pigments are first printed to a convex surface of a plastic mold. Material for the lens is then dropped onto the concave surface of the plastic mold. The mold then spins in a determined speed for a determined period of time, such that a desired radius surface is formed. A pigment composition is found such that the pigment composition will not dissolve to the lens material during the spinning. This invention also discloses the contact lens prepared according to the method of this invention.






Fig. 2

EP 0 983 837 A2

Description**FIELD OF THE INVENTION**

- 5 [0001] The present invention relates to a method for preparation of a colored contact lens, especially to a method to prepare a contact lens with an embedded pattern as well as pigment composition suited in the method and the colored contact lens prepared according to the method.

BACKGROUND OF THE INVENTION

- 10 [0002] The contact lens is a useful vision correction instrument for people having defects in vision. The contact lens makes it possible for a person to avoid the inconvenience of the glasses.
- [0003] A method for the mass production of the contact lens is called "spincasting". It was invented by a Czech company, Československa Akademie Ved, in 1961 and was patented in USA with the patent number of 3,660,545. The spin-
- 15 casting technology was later developed and was widely adopted in the industry. After polymers were used as materials of the contact lens, the manufacture cost of the contact lens was dramatically reduced. As a result, disposable contact lenses are possible and widely used by the consumers. Recently contact lenses with colored appearance were created. The color contact lens functions as a vision correction instrument and a facial adornment.
- [0004] US patent application series number 07/430,222 (assigned to Schering Corporation) related to a colored con-
- 20 tact lens having very natural appearance. This invention disclosed a lens having a non-opaque pupil section and an iris section that is at least partially opaque and comprised of two portions. The portions and sections of the contact lens contained shades with different patterns and colors so to provide a "very natural" appearance.
- [0005] In the above and other inventions for the preparation of the colored contact lens, the inventors tried to provide contact lenses with patterns that made the iris of the wearers to perform a desired appearance with colors. In the pre-
- 25 paration of the colored contact lens, one or more pigments were printed to the convex surface of the contact lens to form a particular pattern. If more than one pigment is used, the pigments were printed in sequence, with one pigment overlapping or non-overlapping with another. A contact lens so prepared has an extruded pigment layer on its convex surface. Sometimes the thickness of the pattern is several times that of one pigment layer.
- [0006] Although the thickness of the pigment layer may be very thin (e.g., 0.01m/m-0.08m/m), wearer of the contact
- 30 lens so prepared may feel the existence of the pigment layer(s). In order to avoid damages to the eyes of the wearer, the conventional art used pigments containing non-organic minerals, such as TiO_2 . Although the diameter of the mineral particles may be up to about 5 μm , the pigment may peel off in piece under the friction of the eyelid. The peeled pigment pieces may also cause damages to the cornea of the wearer.
- [0007] It is thus a need in the industry to have a colored contact lens wherein a colored pattern is embedded in the
- 35 lens. It is also a need in the industry to have a colored contact lens without extruded pigment layers. It is also a need to have a pigment composition suited in the preparation of colored contact lens without extruded pigment layers.

OBJECTIVES OF THE INVENTION

- 40 [0008] The objective of this invention is to provide a novel method for preparation of a colored contact lens without extruded pigment layers.
- [0009] Another objective of this invention is to provide a method for preparation of a colored contact lens with an embedded pattern.
- [0010] Another objective of this invention is to provide a colored contact lens prepared according to the above meth-
- 45 ods.
- [0011] Another objective of this invention is to provide a pigment composition suited in the method and the contact lens described above.

SUMMARY OF THE INVENTION

- 50 [0012] According to the method for preparation of colored contact lens of this invention, pigments are first printed to the plastic mold for the contact lens so that the pigments are distributed on the concave surface of the plastic mold. Material for the lens is then dropped onto the concave surface of the plastic mold. The mold then spins in a determined speed for a determined period of time, such tat the lens material is spread on the concave surface of the plastic mold
- 55 to form a desired radius surface. The lens is ten solidified under a UV lamp. A contact lens with an embedded colored pattern is thus prepared. This invention also discloses the contact lens prepared according to the preparation method of this invention.
- [0013] The above and other objectives and advantages may be clearly understood from the detailed description by

referring to the following drawings.

IN THE DRAWINGS

[0014]

Fig. 1 illustrates the flow chart of the method for preparation of colored contact lens of the invention.

Fig. 2 illustrates the steps of the method for preparation of colored contact lens of the invention wherein (a) shows a plastic mold applied with pigments, (b) shows a colored contact lens with a dazzling appearance being prepared and (c) shows a colored contact lens with a dazzling appearance prepared from the method of this invention.

Table I illustrates possible combinations of pigments that are applicable in the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0015] In the conventional art, materials for the contact lens include hydrophilic high molecular polymers, such as hydroxyethyl methacrylate (HEMA). The pigment may comprise a pigment composition, which comprises a pigment, a dispersing agent and a binding polymer.

[0016] While a colored contact lens with an embedded pattern will be prepared, at least the following questions shall be considered.

1. In order to embedded the pigment composition in the contact lens, the adhesive forces between the pigment and the lens must be strong and long-lasting enough, such that the pigment won't slip off the lens during the slipping and the application; But

2. During the preparation of the colored contact lens, the adhesive forces between the pigment composition and the plastic mold must be strong enough, such that particles of the pigment composition won't be removed to their respective position under the high shearing forces generated from the spinning.

[0017] These requirements are obviously in conflict.

[0018] Although it is not intended to limit the scope of this invention, the inventor has found that a certain pigment compositions may provide strong adhesive forces between the pigment composition and the plastic mold during the spinning, and between the pigment composition and the lens during the slipping and the application of the colored contact lens. In the followings, detailed description of the pigment composition, and the method for preparation of colored contact lens using the pigment composition, will be given.

[0019] Fig. 1 illustrates the flow chart of the method for preparation of colored contact lens of the invention. Fig. 2 illustrates the steps of the method for preparation of colored contact lens of the invention wherein (a) shows a plastic mold applied with pigments, (b) shows a colored contact lens with a dazzling appearance being prepared and (c) shows a colored contact lens with a dazzling appearance prepared from the method of this invention.

[0020] As shown in Fig. 1, in the preparation of the colored contact lens of this invention, a pigment composition is prepared first at 101. The pigment composition suited for this invention comprises at least one pigment, a dispersing agent and a binding polymer.

[0021] Suited dispersing agents for this invention include: monomers or pre-polymers of acrylic resins and other suited dispersing agents. Examples include: hydroxyethyl methacrylate (HEMA), hydroxypropyl methacrylate (HPMA), Methyl methacrylate (MMA) and methyl methacrylate (MMA), glyceryl methacrylate (GMA) etc.

[0022] Suited binding polymers for this invention include: acrylic emulsified pre-polymers, hydroxyethyl methacrylate (HEMA), 2-ethoxyethyl methacrylate (EOEMA), methylacrylic acid (MMA), isopropanol (IPA) and cyclopentanone. Functions of the binding polymers include to generate hydrogen bonds between the lens material and the pigment composition and to generate van der Waals' forces between the lens material and the plastic mold under the supply of ultra-violet light. The van der Waals' forces keep the pigment composition adhered to the plastic mold during the processing of the lens, without being dissolved to the lens material.

[0023] Suited pigments include C.I. Pigment white 6, C.I. pigment blue 15:4, C.I. pigment green 7, C.I. pigment violet 23, C.I. pigment yellow 42 and C.I. pigment Brown. In the embodiments of the present invention, the pigment composition may be composed according to the actual needs. Table I illustrates possible combinations of pigments that are applicable in the present invention. Other pigments, combinations and ratios may also be used in this invention and provide similar effects. In this table, other components of the pigment composition are also shown for reference.

Table I

ratio	color	Crystal	Jade	Violet	Cappuccino	Pearl
material		Blue	Green		or Hazel	Gray
Rutile TiO_2 (C.I. pigment white 6)		20~40%	15~35%	20~45%	0~20%	25~35%
Phtalocyanine Blue (C.I. pigment Blue 15:4)		3~15%				1~8%
Phtalocyanine Green (C.I. pigment Green 7)			15~35%			
Dioxazin Violet (C.I. pigment Violet 23)				3~10%		
Iron Oxide (C.I. pigment Yellow 42)			0~5%		10~30%	
(C.I. pigment Brown)					4~20%	3~10%
biding polymer		50~75%				
lens material		5~25%				
dispersing agent		1~8%				

[0024] In this step 101, the pigment compositions may be that as shown in Table I. At 102 the pigment composition is printed onto the concave surface of a plastic mold. A distribution of the pigment composition or a pattern is then formed on the concave surface of the plastic mold. Here, several pigment compositions may be applied to the plastic mold in sequence to provide a number of colors to the colored contact lens. In other words, the pattern may comprise sub-patterns in different colors. For purpose of convenience, the applied pigments may be less than three kinds. Of course, more than three pigments may be applied, if desirable.

[0025] Fig. 2 illustrates the steps of the method for preparation of colored contact lens of the invention. In fig. 2, (a) shows a plastic mold 1 applied with pigments 2.

[0026] At 103 a certain quantity of lens material 3 is dropped into the concave surface of the plastic mold 1. In some embodiments of this invention, the plastic mold is made of PVC (polyvinyl chloride). Other material may also be used to prepare the mold. The concave surface of the plastic mold 1 may be a spheric or an aspheric surface or other designs or shapes. Materials for the lens may be HEMA, as described above, or other applicable materials.

[0027] At 104 the plastic mold 1 is spun at a determined speed such that the lens material 3 is spread to the concave surface of the plastic mold 1 and form a desired radius surface, due to the centrifugal force of the spinning. The pigment particles will not be positioned at the liquid-spin fluid surface, i.e., it will not extrude from the base curve of the lens. As a result, the pigment will be buried inside the lens. Fig. 2 (b) shows a colored contact lens with an embedded pattern so prepared.

[0028] At 105 a ultra violet lamp 4 above the plastic mold 1 is turned on to solidify the lens material 3, and so the pattern of the pigment composition 2 (see Fig. 2 (a)). The solidification is continued for about 2-10 minutes. At 106, stop the spinning and remove the plastic mold/lens assembly to an annealing chamber (not shown) to be annealed. At 107 edging of the lens is conducted and at 108 hydration and stripping are operated. A colored contact lens is then accomplished. Fig. 2 (c) shows a colored contact lens with an embedded pattern prepared according to the method of this invention.

EFFECTS OF THE INVENTION

[0029] The contact lens so prepared is observed under a microscope. The pigment and its pattern is distributed inside the lens. The lens has a smooth surface, without any defects.

[0030] The plastic mold after stripping is also observed under a microscope. The convex surface of the plastic mold appears clean and smooth. No residual of pigment is found.

[0031] The pigment that provide the colored pattern is embedded in the lens material. No extrusions from the surface of the lens is found. The pigment won't shell out to cause damages to wearers of the lens.

[0032] In the above description of the embodiment of this invention, the spincasting approach is given for example, for purpose of description. The invented method, however, is applicable to the extrusion approach and other approaches.

[0033] As the present invention has been shown and described with reference to preferred embodiments thereof, those skilled in the art will recognize that the above and other changes may be made therein without departing from the spirit and scope of the invention.

Claims

1. A method for the preparation of colored contact lens, comprising:

prepare a pigment composition;
 apply said pigment composition to a convex surface of a mold to form a pattern;
 drop a quantity of lens material to said convex surface of said mold;
 spin said mold such that said lens material is spread on said convex surface of said mold to form a radius surface; and
 solidify said lens material and said pigment composition;
 characterized in that said pigment composition comprises approximately 10-50 (weight)% of pigment, 50-70 (weight)% binding polymer and 0-10 (weight)% dispersing agent.

2. The method according to claim 1 wherein said pigment composition is applied to said convex surface through secondary conversion.

3. The method according to claim 1 or 2 wherein said dispersing agent is at least one selected from acrylic resin, hydroxyethyl methacrylate (HEMA), hydroxypropyl methacrylate (HPMA), Methyl methacrylate (MMA), methyl methacrylate (MMA) and glyceryl methacrylate (GMA).

4. The method according to claim 1 or 2 wherein said binding polymer is at least one selected from acrylic emulsified pre-polymers, hydroxyethyl methacrylate (HEMA), 2-ethoxyethyl methacrylate (EOEMA), methylacrylic acid (MMA), isopropanol (IPA) and cyclopentanone.

5. A method for the preparation of colored contact lens, comprising:

prepare a pigment composition;
 apply said pigment composition to a convex surface of a mold to form a pattern;
 drop a quantity of lens material to said convex surface of said mold;
 apply a die with a concave surface corresponding to said convex surface of said mold to said convex surface of said mold such that said lens material forms a radius surface; and
 rotate said die and said mold relatively and solidify said lens material and said pigment composition;
 characterized in that said pigment composition comprises approximately 10-50 (weight)% of pigment 50-70 (weight)% binding polymer and 0-10 (weight)% dispersing agent.

6. The method according to claim 5 wherein said pigment composition is applied to said convex surface through secondary conversion.

7. The method according to claim 5 or 6 wherein said dispersing agent is at least one selected from acrylic resin, hydroxyethyl methacrylate (HEMA), hydroxypropyl methacrylate (HPMA), Methyl methacrylate (MMA), methyl methacrylate (MMA) and glyceryl methacrylate (GMA).

8. The method according to claim 5 or 6 wherein said binding polymer is at least one selected from acrylic emulsified

EP 0 983 837 A2

pre-polymers, hydroxyethyl methacrylate (HEMA), 2-ethoxyethyl methacrylate (EOEMA), methylacrylic acid (MMA), isopropanol (IPA) and cyclopentanone.

- 5 9. A contact lens comprises a lens with a concave surface and a convex surface and a pattern comprising at least one pigment and embedded inside said convex surface wherein said pigment of said pattern comprises approximately 10-50 (weight)% of pigment, 50-70 (weight)% binding polymer and 0-10 (weight)% dispersing agent.
- 10 10. A pigment composition for coloring a contact lens comprising approximately 10-50 (weight)% of pigment, 50-70 (weight)% binding polymer and 0-10 (weight)% dispersing agent.

10

15

20

25

30

35

40

45

50

55







Fig. 1



(a)



(b)



(c)

Fig. 2

Table I

ratio	color	Crystal	Jade	Violet	Cappuccino	Pearl
material		Blue	Green		or Hazel	Gray
Rutile TiO_2 (C.I. pigment white 6)		20~40%	15~35%	20~45%	0~20%	25~35%
Phtalocyanine Blue (C.I. pigment Blue 15:4)		3~15%				1~8%
Phtalocyanine Green (C.I. pigment Green 7)			15~35%			
Dioxazin Violet (C.I. pigment Violet 23)				3~10%		
Iron Oxide (C.I. pigment Yellow 42)			0~5%		10~30%	
(C.I. pigment Brown)					4~20%	3~10%
biding polymer		50~75%				
lens material		5~25%				
dispersing agent		1~8%				

7.
(

(19)



Europäisches Patentamt
European Patent Office
Offic européen des brevets



(11)

EP 0 983 837 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
02.01.2002 Bulletin 2002/01

(51) Int Cl.7: B29D 11/00, G02B 1/04

(43) Date of publication A2:
08.03.2000 Bulletin 2000/10

(21) Application number: 98123191.3

(22) Date of filing: 04.12.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 02.09.1998 US 145654

(71) Applicant: INNOVA, Inc
Hsinchu (TW)

(72) Inventor: Wang, Joe
Hsinchu (TW)


(74) Representative:
Winter, Brandl, Fürniss, Hübner, Röss, Kaiser,
Polte Partnerschaft
Patent- und Rechtsanwaltskanzlei
Alois-Steinecker-Strasse 22
85354 Freising (DE)

(54) Method for preparation for colored contact lens

(57) A method for preparation of colored contact lens with an embedded pattern is disclosed. Pigments (2) are first printed to a convex surface of a plastic mold (1). Material (3) for the lens is then dropped onto the concave surface of the plastic mold. The mold then spins in a determined speed for a determined period of time, such that a desired radius surface is formed. A pigment composition is found such that the pigment composition will not dissolve to the lens material during the spinning. This invention also discloses the contact lens prepared according to the method of this invention.



(a)



(b)



(c)

Fig. 2



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 12 3191

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X A	US 5 034 166 A (RAWLINGS DAVID L ET AL) 23 July 1991 (1991-07-23) * column 1, line 1 - line 22 * * column 5, line 65 - column 6, line 10 * * column 6, line 21 - line 27 * * column 6, line 44 - line 46 * * column 7, line 19 - line 38 * * column 10, line 14 - line 22; figure 2 * ----	1-4 5	B29D11/00 G02B1/04
X	US 5 120 121 A (BAO QI-BIN ET AL) 9 June 1992 (1992-06-09) * column 1, line 1 - line 12 * * column 4, line 5 - line 29 * * column 9, line 55 - line 64 * * column 11, line 45 - line 59 * * column 12, line 5 - line 8 * * column 12, line 29 - line 49 * * column 14, line 41 - column 15, line 6 * * column 17, line 13 - line 22; figures 6-8 * ----	1-4	
X A	US 4 746 691 A (FUHRMAN ARI) 24 May 1988 (1988-05-24) * column 1, line 1 - line 16 * * column 1, line 27 - line 33 * * column 4, line 32 - line 68 * ----	9,10 1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B29D G02C B29C
A	US 4 639 105 A (NEEFE CHARLES W) 27 January 1987 (1987-01-27) * claim 1 * -----	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 6 November 2001	Examiner Ingelg rd, T.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 12 3191

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-11-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5034166 A	23-07-1991	AT 102121 T	15-03-1994
		AU 627473 B2	27-08-1992
		AU 3820089 A	25-01-1990
		BR 8903570 A	13-03-1990
		CN 1040542 A ,B	21-03-1990
		DE 68913380 D1	07-04-1994
		DE 68913380 T2	01-06-1994
		DK 363789 A	22-01-1990
		EP 0352134 A2	24-01-1990
		ES 2054001 T3	01-08-1994
		IL 90933 A	18-08-1992
		JP 2134612 A	23-05-1990
		JP 2837696 B2	16-12-1998
		NZ 229896 A	25-06-1992
		US 5120121 A	09-06-1992
		US 5116112 A	26-05-1992
		ZA 8905331 A	28-03-1990
US 5120121 A	09-06-1992	US 5034166 A	23-07-1991
		AT 126360 T	15-08-1995
		AU 633890 B2	11-02-1993
		AU 5224490 A	04-10-1990
		BR 9001396 A	09-04-1991
		CA 2013218 A1	28-09-1990
		CN 1046612 A ,B	31-10-1990
		DE 69021422 D1	14-09-1995
		DE 69021422 T2	29-02-1996
		EP 0390443 A1	03-10-1990
		ES 2076305 T3	01-11-1995
		IE 69173 B1	07-08-1996
		IL 93897 A	28-11-1994
		JP 2975040 B2	10-11-1999
		JP 3015020 A	23-01-1991
		NZ 233063 A	27-09-1993
		ZA 9002350 A	27-03-1991
		AT 102121 T	15-03-1994
		AU 627473 B2	27-08-1992
		AU 3820089 A	25-01-1990
		BR 8903570 A	13-03-1990
		CN 1040542 A ,B	21-03-1990
		DE 68913380 D1	07-04-1994
		DE 68913380 T2	01-06-1994
		DK 363789 A	22-01-1990
		EP 0352134 A2	24-01-1990
		ES 2054001 T3	01-08-1994
		IL 90933 A	18-08-1992

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 12 3191

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-11-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5120121 A		JP 2134612 A	23-05-1990
		JP 2837696 B2	16-12-1998
		NZ 229896 A	25-06-1992
		US 5116112 A	26-05-1992
		ZA 8905331 A	28-03-1990
US 4746691 A	24-05-1988	CA 1227589 A1	29-09-1987
		DE 3381171 D1	08-03-1990
		DE 101504 T1	20-12-1984
		EP 0101504 A1	29-02-1984
		WO 8302777 A1	18-08-1983
		US 4638025 A	20-01-1987
US 4639105 A	27-01-1987	US 4416837 A	22-11-1983
		US 4534915 A	13-08-1985
		US 4590018 A	20-05-1986
		US 4578230 A	25-03-1986
		US 4597918 A	01-07-1986
		US 4637791 A	20-01-1987
		US 4607428 A	26-08-1986
		US 4659522 A	21-04-1987
		US 4615593 A	07-10-1986

EPO FORM P449

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

USA Penary
G-1111

November 8, 2002

RE: Search Report - **VIN 571 EPO**

To: ~~LH/KH~~

Search report procedure is to docket three months from the date of the agents letter, OFFICE ACTION-REFERENCE CITED.

This is done for our attorney's benefit in case they would like to comment on the examiners remarks.

If no action is going to be taken, please advise me and I will remove the search report item from your docket.

Thank you,

Artrena Smith

REMINDER: All references cited in all countries (including U.S.A.), must be supplied to Israel, if the application was filed in Israel.

